

TECHNICAL DATA SHEET

PRODUCT	CLW9201
Max Service Temperature	1700°C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	90 – 92
CaO	7 – 9
SiO ₂	0.5 – 1.0
Water Required to Mix (%)	18 - 20
PHYSICAL PROPERTIES	
After Drying at 110 °C for 24 hrs	
Bulk Density	1.4 ± 0.1 g/cm ³
Cold Compressive Strength	100 kg/cm ²
Linear Change	0.0 %
After Preheating at 1500 °C for 5 hrs	
Bulk Density	1.4±0.1 g/cm ³
Cold Compressive Strength	350 kg/cm ²
Linear Change	≤ 1 %
Water/Mix Temperature	20±5 °C
Mixing Time (min): Dry/Wet	2/5

The data given in this technical information sheet have been determined as average values on test specimens.