

TECHNICAL DATA SHEET

PRODUCT	LCC 9001
Max Service Temperature	1750 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	89 - 91
SiO ₂	6 - 8
Water Required to Mix (%)	4.5 – 5.5
PHYSICAL PROPERTIES	
After Drying at 110 °C for 24 hrs	
Bulk Density	3.00 g/cm ³
Cold Compressive Strength	1000 kg/cm ²
Linear Change	0.0 %
After Preheating at 1500 °C for 5 hrs	
Bulk Density	3.00 g/cm ³
Cold Compressive Strength	1200 kg/cm ²
Linear Change	±1 %
Water/Mix Temperature	20±5 °C
Mixing Time (min): Dry/Wet	2/5

The data given in this technical information sheet have been determined as average values on test specimens.