

## TECHNICAL DATA SHEET

<b>PRODUCT</b>	<b>MAS3301</b>
<b>Max Service Temperature</b>	1350 °C
<b>CHEMICAL COMPOSITION</b>	%
Al <sub>2</sub> O <sub>3</sub>	30 - 33
SiO <sub>2</sub>	50 – 53
Fe <sub>2</sub> O <sub>3</sub>	≤ 3.5
L.O.I	11 - 12
<b>PHYSICAL PROPERTIES</b>	
Grain size	> 325 μ=1% max, > 90μ =15 % max
Type of bond	ceramic
Water required	27 - 30 %

The data given in this technical information sheet have been determined as average values