

TECHNICAL DATA SHEET

PRODUCT	MHS 4501
Max Service Temperature	1500 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	44 - 46
SiO ₂	45 - 57
Fe ₂ O ₃	≤ 2.5
L.O.I	4 - 5
PHYSICAL PROPERTIES	
Grain size	> 325 μ=1% max, > 90μ =15 % max
Type of bond	ceramic
Water required	25 - 27 %

The data given in this technical information sheet have been determined as average values