

TECHNICAL DATA SHEET

PRODUCT	MHS 4802
Max Service Temperature	1500 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	46 - 48
SiO ₂	43 - 55
Fe ₂ O ₃	≤ 2.5
L.O.I	4 - 5
PHYSICAL PROPERTIES	
Grain size	>325 μ=1% max, > 90μ =15 % max
Type of bond	ceramic
Water required	23 - 25 %

The data given in this technical information sheet have been determined as average values