

TECHNICAL DATA SHEET

PRODUCT	MHS 6501
Max Service Temperature	1675 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	64 - 66
SiO ₂	24 - 26
Fe ₂ O ₃	≤ 2.5
L.O.I	3.5 – 4.5
PHYSICAL PROPERTIES	
Grain size	> 325 μ=1% max, > 90μ =15 % max
Type of bond	ceramic
Water required	22 - 24 %

The data given in this technical information sheet have been determined as average values