

TECHNICAL DATA SHEET

PRODUCT	MHS 7001
Max Service Temperature	1700 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	69 - 71
SiO ₂	20 - 22
Fe ₂ O ₃	≤ 2.5
L.O.I	3 - 4
PHYSICAL PROPERTIES	
Grain size	> 325 μ=1% max, > 90μ =15 % max
Type of bond	ceramic
Water required	20 - 22 %

The data given in this technical information sheet have been determined as average values