

TECHNICAL DATA SHEET

PRODUCT	MHS 8001
Max Service Temperature	1750 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	74 - 76
SO ₂	16 - 18
Fe ₂ O ₃	≤ 2.5
L.O.I	2.5 – 3.0
PHYSICAL PROPERTIES	
Grain size	> 325 μ=1% max, >90μ =15 % max
Type of bond	ceramic
Water required	20 - 22 %

The data given in this technical information sheet have been determined as average values