

TECHNICAL DATA SHEET

CLASSIFICATION	ASTM C-1655
PRODUCT	MHS ٩٠٠1
Max Service Temperature, ASTM C -24	18٠0 °C
CHEMICAL COMPOSITION, ASTM C- 573	%
Al ₂ O ₃	86 - 90
SO ₂	8 - 12
Fe ₂ O ₃	≤ 1.0
L.O.I	2.0 – 2.5
PHYSICAL PROPERTIES	
Grain size	> 325 μ=1% max, >90μ =15 % max
Type of bond	ceramic
Water required	20 - 22 %

The data given in this technical information sheet have been determined as average values