

TECHNICAL DATA SHEET

PRODUCT	MPR 8001
Max Service Temperature	1750 °C
CHEMICAL COMPOSITION	%
Al ₂ O ₃	78 - 80
SiO ₂	7 - 9
P ₂ O ₅	6.5 - 7.5
Fe ₂ O ₃	≤ 2.0
PHYSICAL PROPERTIES	
Grain size	> 500 μ=1% max
Type of bond	chemical - ceramic
Shelf life	6 months from the date of production

The data given in this technical information sheet have been determined as average values